



## LEIPA Classic White C

is an uncoated white top testliner based on 100% recycled waste paper. The higher strength gives your product an extra stability and is underlined by a higher surface quality, what guarantees a brilliant printability.

Valid from Dezember 2021

Properties	Unit	Standard	Target Figures										Tolerances
Grammage	g/m <sup>2</sup>	ISO 536	100	110	115	120	125	130	135	140	150*	± 2%	
Moisture	%	ISO 287	7,5	7,5	7,5	7,5	7,5	7,5	7,5	7,5	7,5	± 1	
Burst resistance	kPa	ISO 2758	170	190	195	200	210	220	230	240	250	-5%	
SCT (CD)	kN/m	ISO 9895	1,2	1,4	1,4	1,5	1,6	1,7	1,8	1,9	2,0	-5%	
Cobb <sub>60</sub> TS	g/m <sup>2</sup>	ISO 535	35	35	35	35	35	35	35	35	35	≤ 50	
Brightness TS	%	ISO 2470-2	72	72	72	72	72	72	72	72	72	-2	
Roughness (Bendtsen) TS	ml/ min	ISO 8791-2	300	300	300	300	300	300	300	300	300	≤ 350	

\*preliminary

Are you interested?  
Please contact us:

e. sales@leipa.com  
t. +49 3332 24-3000



[www.leipa.com](http://www.leipa.com)

### Certifications



The mark of  
responsible forestry



### Carbon footprint

	DE	Europe	USA
Results by transport scenario [kg CO <sub>2</sub> e/ton of paper]	793,6	807,7	942,8

Based on the EURO-GRAPH/ CEPI framework