

LEIPA Excellence

LEIPA Excellence with glossy surface provides the excellent quality requirements for gift wrapping.

Characteristics

- » Two surface finishes for the individual emotional experience of wrapping a gift package
- » Perfect printability and runability for gift wrap images
- » Highest opacity

Key Benefits

- » FSC®-Recycling and PEFC certified

Typical Applications

- » Gift wrapping

| Properties | Unit | Standard | Target Figures | | | | | | | | Tolerances |
|---------------------|------------------|------------|----------------|------|------|------|------|------|------|------|------------|
| Grammage | g/m ² | ISO 536 | 51 ** | 54 | 57 | 60 | 65 | 70 | 80 | 90 | ± 4% |
| Brightness | % | ISO 2470 | 78 | 78 | 78 | 80 | 80 | 80 | 82 | 82 | ± 4% |
| Opacity | % | DIN 53146 | ≥ 90 | ≥ 92 | ≥ 92 | ≥ 92 | ≥ 92 | ≥ 92 | ≥ 94 | ≥ 94 | |
| Gloss | % | ISO 8254-1 | ≥ 43 | ≥ 43 | ≥ 43 | ≥ 43 | ≥ 43 | ≥ 43 | ≥ 43 | ≥ 43 | |
| Tensile strength MD | km | ISO 1924-2 | 5,0 | 5,0 | 5,0 | 5,0 | 5,0 | 5,0 | 5,0 | 5,0 | ≥ 4,0 |
| Thickness | µm | ISO 534 | 44,0 | 46,0 | 49,0 | 51,5 | 56,0 | 60,0 | 70,5 | 79,0 | ± 10% |

All values are measured under standard climate condition (23°C, 50% RH). Our measurement devices are included within the CEPI cycle. The given technical values are for information purposes only. LEIPA Georg Leinfelder GmbH reserves the right to change product characteristics in accordance with research and market developments. The paper qualities marked with ** are on demand. Please contact us, if you are interested.

Prepress

| L* a* b* target values | L* | a* | b* |
|------------------------|----|----|----|
| ISO 5631-3 (D50/2°) | 90 | 0 | 1 |

ICC-Profile

PSO LWC Standard (ECI)

Specification valid from January 2026

Certifications



The mark of responsible forestry



Are you interested? Please contact us.

www.leipa.com/graphicpaper

sales@leipa.com

+49 3332 24-3000

